BLUESCOPE ZACS® G300 Steel

Revision 4

October 2022

This literature supersedes all previous issues



Metallic Coated - MC

Structural - S

GENERAL DESCRIPTION

BlueScope ZACS® G300 steel is a continuous hot-dipped aluminium/zinc alloy-coated structural steel with a regular spangle surface and a guaranteed minimum yield strength of 300MPa with good ductility. Suitable for roll-forming to a minimum internal diameter of 1t.

TYPICAL USES

Thin-gauge and economical roll formed roofing and wall cladding, and awning for retail segment. For material selection advice, please contact your nearest BlueScope sales office.

MALAYSIAN STANDARD

MS 1196

GUARANTEED PROPERTIES OF STEEL BASE

| MECHANICAL PROPERTIES | GUARANTEED MINIMUM (LONGITUDINAL TENSILE) |
|----------------------------------|--|
| Yield Strength, MPa | 300 |
| Tensile Strength, MPa | 340 |
| Elongation on 50mm (≥ 0.60mm), % | 20 |

CHEMICAL COMPOSITION OF STEEL BASE

| CHEMICAL PROPERTIES | GUARANTEED MAX % |
|---------------------|------------------|
| Carbon – C | 0.25 |
| Manganese – Mn | 1.50 |
| Phosphorus – P | 0.035 |
| Sulphur – S | 0.035 |

METAL COATING ADHESION - 180° BEND TEST

| AZ90 1t | |
|---------|--|

Notes

Where t = the diameter of mandrel in terms of thickness of product.

FIRE HAZARD PROPERTIES - AS/NZS1530.3

| INDEX | RANGE | RESULT |
|-----------------------|-------|--------|
| Ignitability Index | 0-20 | 0 |
| Spread Of Flame Index | 0-10 | 0 |
| Heat Evolved Index | 0-10 | 0 |
| Smoke Developed Index | 0-10 | 0-1 |

DIMENSIONAL CAPABILITIES*

| PREFERRED BASE METAL THICKNESS, mm | MAXIMUM WIDTH, mm |
|---|-------------------|
| 0.20, 0.23, 0.25, 0.28, 0.30, 0.35, 0.40 | 914 |

Notes

NORMAL/OPTIONAL SUPPLY CONDITIONS*

| | NORMAL | OPTIONAL# |
|-------------------|---------------------------|-------------------------------------|
| Coating Class | AZ90 | - |
| Surface Condition | Spangled | Skin Passed |
| Surface Treatment | Passivated & Resin Coated | Passivated & Non-Resin Coated |
| Branding | Branded | Not Branded |

Notes

NS BLUESCOPE MALAYSIA SDN BHD (199101012824 (223136-P))

LEVEL 11, TOWER 8, UOA BUSINESS PARK, NO. 1, JALAN PENGATURĆARA U1/51Å, SEKSYEN U1, 40150 SHAH ALAM, SELANGOR, MALAYSIA T: +603 5022 1000 CUSTOMER CARE: 1 300 88 6288 F: +603 5022 1001 E: ENQUIRIES.MALAYSIA@BLUESCOPE.COM

^{*} Not every combination of thickness and width may be available. Supply conditions may be subject to dimensional restrictions and are subject to BlueScope Sales and Marketing confirmation. Slitting and shearing available on request from BlueScope Sales Offices. For requirements outside the standard product range please contact your local Sales Office.

[#] Optional supply conditions may be subject to dimensional restrictions.

^{*} The dimensional tolerances for thickness, width flatness and camber shall be in accordance with the requirements of ISO 16163.

BLUESCOPE ZACS® G300 Steel

Revision 4

October 2022

This literature supersedes all previous issues



Metallic Coated - MC

Structural - S

FABRICATING PERFORMANCE

| METHOD | RATING | METHOD | RATING |
|----------|--------|-----------------------|--------|
| Bending | 5 | Roll Forming | 5 |
| Drawing | 2 | Welding | 4* |
| Pressing | 2 | Painting Pretreatment | 5 |

Notes

Where: 1 = Limited to 5 = Excellent or NR = Not Recommended * Welding design must allow for some strength reduction near welds

IMPORTANT INFORMATION

- 1. Spangle variance from coil to coil is an inherent characteristic of metallic alloy coating process and will not affect the performance of the product. It is therefore not a cause for rejection.
- 2. Typical mechanical properties are based on typical product despatched to customers. Note that ductility will decline through a natural ageing process during storage and/or paint stoving cycle.
- 3. Material should be used promptly (within six months) to avoid the possibility of a storage related corrosion. Roll-forming mark does not affect the performance of ZINCALUME® steel. For selection of the most appropriate metallic coated steel, please refer to technical bulletins TB1a, TB1b, CTB21 and CTB22. For storage, roll-forming lubricants, and other information, please refer to the Technical Bulletins.
- 4. We recommend storage in bore vertical orientation to prevent coil slump. If you wish to know more about the consequence of coil slump, please refer to our Fact Sheet 2, link: https://www.nsbluescope.com/my/wp-content/uploads/sites/7/2020/10/Fact-Sheet-Coil-Slump.pdf.
- 5. Use of aged coil might lead to quality issue during roll-forming process. To determine if warranties apply for aged coil, please contact your nearest BlueScope sales office for advice.

LEVEL 11, TOWER 8, UOA BUSINESS PARK, NO. 1, JALAN PENGATURĆARA U1/51Å, SEKSYEN U1, 40150 SHAH ALAM, SELANGOR, MALAYSIA T: +603 5022 1000 CUSTOMER CARE: 1 300 88 6288 F: +603 5022 1001 E: ENQUIRIES.MALAYSIA@BLUESCOPE.COM