# ZINCALUME® G250 steel

June 2020

This literature supersedes all previous issues

## Metallic Coated - MC

## **GENERAL DESCRIPTION**

ZINCALUME<sup>®</sup> G250 steel is a hot-dipped zinc-aluminium 55% alloy-coated structural steel and a guaranteed minimum yield strength of 250 MPa with good ductility. Suitable for roll-forming to a minimum internal radius of 1t.

## **TYPICAL USES**

Roll-formed decking, and walling, rain water goods, tubing, garage doors, gutters, sign and general application

## **STANDARDS**

Certified Standards – TIS. 2228-2559 Reference Standards - AS 1397, ASTM A 792/A 792M, JIS G3321 AS 1365, ASTM A 924/A 924M

## **GUARANTEED PROPERTIES OF STEEL BASE**

MECHANICAL PROPERTIES	GUARANTEED MINIMUM
Yield Strength, MPa	250
Tensile Strength, MPa	320
Elongation on 50mm (≥ 0.60mm), %	25

## CHEMICAL COMPOSITION OF STEEL BASE

CHEMICAL PROPERTIES	GUARANTEED MAX %
Carbon - C	0.20
Phosphorus - P	0.04
Manganese – Mn	1.20
Sulphur - S	0.03

#### METAL COATING ADHESION - 180° BEND TEST

COATING CLASS	COATING ADHESION
AZ150	Ot
AZ200	Ot

Where t = the diameter of mandrel in terms of thickness of product.

### **DIAMENSIONAL CAPABILITIES**

THICKNESS RANGES (mm)	MAX. WIDTH (mm)
0.30-1.00	1260
1.01-1.20	1220

Notes: These dimensions are a reflection of technical capability to produce. Supply conditions may be subject to dimensional restrictions and is subject to BlueScope Sales and Marketing confirmation. Slitting and shearing available on request from BlueScope Sales Offices. For requirements outside the standard product range please contact your local Sales Office.

### **FABRICATING PERFORMANCE**

METHOD	RATING	METHOD	RATING
Bending	5	Lock Forming	NR
Drawing	2	Welding	4
Pressing	2	Painting Pretreatment	5
Roll Forming	5		

Where: 1 = Limited to 5 = Excellent or NR = Not Recommended

IMPORTANT INFORMATION

Typical mechanical properties are based on typical product despatched to customers. Note that ductility will decline through a natural ageing process during storage and/or paint storing cycle. Material should be used promptly (within six months) to avoid the possibility of a storage related corrosion. For selection of the most appropriate metallic coated steel, please refer to technical bulletins TB-1a, TB-1b, CTB-21 and CTB-22. For storage, rollforming lubricants and other information please refer to the Technical Bulletins.

#### NS BLUESCOPE (THAILAND) LIMITED

Address :	188 Spring Tower 14th floor Unit no. 1 – 5, Phayathai Road, Tung Phayathai Subdistrict, Ratchathewi District, Bangkok 10400	
Contact Phone:	+662 333 3000	www.nsbluescope.com

ZINCALUME<sup>®</sup>, Clean COLORBOND<sup>®</sup>, PRIMA<sup>®</sup>, BLUESCOPE ZACS<sup>®</sup>, JINGJOE LEK<sup>®</sup>,ZACS<sup>®</sup>, CRP ANTIBACTERIAL<sup>™</sup> SD, SHUTTEREX<sup>®</sup>, ENDUROCORE<sup>™</sup>, TRUECORE<sup>®</sup> and BlueScope are registered trademarks of BlueScope Steel Limited ABN 16 000 011 058. Please ensure you have the current data sheet for this product as displayed at www.nsbluescope.com



#### FIRE HAZARD PROPERTIES

INDEX	RANGE	RESULT
Ignitability Index	0-20	0
Spread Of Flame Index	0-10	0
Heat Evolved Index	0-10	0
Smoke Developed Index	0-10	0-1

### NORMAL/OPTIONAL SUPPLY CONDITIONS

	NORMAL	OPTIONAL
Coating Class	AZ150	AZ200
Surface Condition	Spangled	
Surface Treatment	Passivated & Resin coated	
Branding	Branded	Not branded

#### Important Notes

Optional supply conditions may be subject to dimensional restrictions